

### DESCRIPTION

**CANTOL 139 FLEXIBLE BROADCAST PRIMER** is a two component 100% solids epoxy designed for sealing traffic surfaces exposed to vehicular or foot traffic. The toughness and elongation eliminate the need to repair hairline cracks. **CANTOL 139 FLEXIBLE BROADCAST PRIMER** is recommended for priming as a crack bridging sealer. This product is formulated for use in a broadcast system as the basecoat prior to installing epoxy mortars or other suitable topcoats.

### FEATURES

- Epoxy Durability
- Repairs Hairline Cracks
- Seals and Repairs
- 100% Solids
- High Traffic Areas
- Broadcast System Base
- No VOC's
- Abrasion Resistant

### DIRECTIONS

#### PRODUCT STORAGE:

- Store product in an area so as to bring the material to normal room temperature before using.
- Continuous storage should be between 60 and 90°F (15.5-32.2°C).
- Low temperatures or temperature fluctuations may cause crystallization.

#### SURFACE PREPARATION:

- The most suitable surface preparation would be a fine brush blast (shot blast) to remove all laitance (fine particles on the surface of fresh concrete) and provide a suitable profile.
- All dirt, foreign contaminants, oil, and laitance must be removed to assure a trouble free bond to the substrate.
- A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' (1.22 x1.22meters) plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating.

#### PRODUCT MIXING:

- This product has a mix ratio of 9.2# (4.17kg) part A to 8.2# (3.72kg) part B or one part A to one part B by volume.
- Standard packages are in pre-measured kits and should be mixed as supplied in the kit.
- We highly recommend that the kits not be broken down unless suitable weighing equipment is available.
- After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free.

#### PRIMING:

Primers may be beneficial in some applications, dependent on performance characteristics and substrate condition, but none are required for product application. Consult with your Cantol Representative.

#### PRODUCT APPLICATION:

- The mixed material can be applied by brush or roller.
- However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained.
- Because this material has a short pot life (15 to 25 minutes), it is beneficial in some applications to remove the material from the mixing pail by pouring the material onto the substrate and spreading it along the floor.
- Spreading out the material will allow the applicator more time to work with the material before it begins to cure.
- Aggregate should be broadcast into the applied material before applying suitable topcoats.
- Maintain temperatures and relative humidity within the recommended ranges during the application and curing process.
- If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating.

### RECOAT OR TOPCOATING:

- We recommend a suitable topcoat be applied only after broadcasting suitable aggregate into the basecoat.
- If you recoat or topcoat this product, you must first be sure that the coating has tacked off before recoating.
- All previous coats that were not applied as a broadcast, should be deglossed to insure a trouble free bond prior to application of recoats or topcoats.
- It is advisable to test topcoats for suitability prior to application when not in a broadcast system.
- Colder temperatures will require more cure time for the product before recoating or topcoating can commence.
- Before recoating or topcoating, check for epoxy blushes (a whitish, greasy film, or deglossing.) If a blush is present, it can be removed by CANTOL EF-90 detergent, cleaner prior to topcoating or recoating.
- Many epoxy coatings and urethanes as well as multiple coats of this product are compatible for use.

### CLEANUP:

Use xylol, xylene, toluene, paint thinner.

### FLOOR CLEANING:

Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area. Best to use Cantol EF-90. If no ill effects are noted, you can continue to clean with the product and process tested.

### RESTRICTIONS:

Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured. It is best to let the floor remain dry for the full cure cycle (2-7 days)

### APPLICATIONS

Recommended for priming with broadcasting as a crack bridging sealer before application of epoxy mortar or topcoats.

### TECHNICAL DATA

**Solids by weight:** 100%

**Solids by volume:** 100%

**Volatile organic content:** zero pounds per gallon

**Colors available:** Clear (gardner 3-4)

**Recommended thickness:** 10-50 mils

**Coverage per gallon:** 32-160 square feet per gallon (0.78 – 3.92 sq. meters) @ 10-50 mils

**Packaging information:** 2 gallon kit (7.57 litres) (volume approximate) 10 gallon kits 37.85 litres) (volume approximate)

**Mix ratio:** 9.2 pounds (1 gallon) (1.10kg/L) part A to 8.2 pounds (1.0 gallon) (0.98kg/L) part B (volumes approx.)

**Shelf life:** 1 year in unopened containers

**Abrasion resistance:** Taber abraser CS-10 callibrase wheel with 1000 gram total load and 500 cycles= 6 mg loss.

**Viscosity:** Mixed = 1,000-1,700 cps (typical)

**DOT CLASSIFICATIONS:** Part A "not regulated"

Part B "CORROSIVE LIQUID N.O.S., 8, UN1760, PGIII"

**Flexural strength:** 2,600 psi @ ASTM D790

**Compressive strength:** 4,100 psi @ ASTM D695

**Tensile strength:** 2,450 psi @ ASTM D638

**Ultimate elongation:** 60%

**Gardner variable impactor:** 160 inch pounds direct- passed

**Adhesion:** 450 psi @ elcometer (concrete failure, no delamination)

**Hardness:** Shore D = 58

# PRODUCT DATA

## CANTOL 139 FLEXIBLE COATING

### CURE SCHEDULE: (70°) (21.11°C):

Pot life (2 gallon volume) .....	15-25 Minutes
Tack free (dry to touch).....	5-8 Hours
Recoat or topcoat .....	8-12 Hours
Light foot traffic .....	12-24 Hours
Full cure (heavy traffic) .....	2-7 Days

### APPLICATION TEMPERATURE:

60-90°F (15.55-32.22°C) with relative humidity below 85%

### CHEMICAL RESISTANCE:

REAGENT	RATING
Acetic Acid 5%	A
Acetic Acid 10%	A
Acetone	A
Ammonia	B
Brake Fluid	A
Ethyl Alcohol	A
Ethylene Glycol Monomethyl Ether	A
Hydrochloric Acid 10%	C
Hydrochloric Acid 36%	A
Methanol	A
Methylene Chloride	A
Methyl Ethyl Ketone (MEK)	A
Nitric Acid 5%	B
Nitric Acid 30%	A
Phosphoric Acid 40%	B
Skydrol	A
Sodium Hydroxide 10%	D
Sodium Hydroxide 50%	D
Sulfuric Acid 10%	C
Water	D
Xylene	A

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. **NOTE:** Extensive chemical resistance information is available through your sales representative.

### PRIMER:

None required

### TOPCOAT:

After broadcasting aggregate into the **CANTOL 139 FLEXIBLE BROADCAST PRIMER**, many suitable toppings can be used. This would include products like CANTOL 321 TWO COMPONENT URETHANE, CANTOL 322 TWO COMPONENT VOC COMPLIANT URETHANE and CANTOL 707 HI-BUILD EPOXY. Check with your Cantol Representative for application details.

### LIMITATIONS:

- \* Clarity of color or gloss may be affected by environmental conditions such as high humidity, low temperatures, or chemical exposure.
- \* It is recommended that a broadcast application be performed with a subsequent topcoat system. This product is not intended as a decorative coating, but merely as a primer for bridging cracks in a broadcast system before topcoating.
- \* This product is not suitable in all chemical environments. When chemical exposure is imminent, a test should be performed to test suitability.
- \* Substrate temperature must be 5°F above dew point.
- \* All new concrete must be cured for at least 30 days prior to application.
- \* Applications with relative humidity above 85% or early water contamination may cause white discolorations to develop.
- \* Improper mixing may result in product failure.
- \* Substrate temperature must be 5°F (3°C) above dew point (temperature at which the air becomes saturated...or 100% humidity).

### PRECAUTIONS

**PART A: WARNING:** Causes irritation. Avoid contact with skin and eyes. Use with adequate ventilation. Wear goggles when using. Wear gloves impervious to chemicals. Wash thoroughly after handling. Keep away from heat, sparks and open flame. Close container after each use. May cause skin sensitization. **FIRST AID:** In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Seek prompt medical attention. Flush skin with soap and water. If ingested, do not induce vomiting. Call a physician. Inhalation: remove to fresh air.

**PART B: DANGER: CORROSIVE.** Avoid contact with skin and eyes. Use with adequate ventilation. Wear goggles when using. Wash thoroughly after handling. Keep away from heat, sparks, and open flame. Close container after each use. May cause skin sensitization. **FIRST AID:** In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Seek prompt medical attention. Flush skin with soap and water. If ingested, do not induce vomiting. Call a physician. Inhalation: remove to fresh air. For industrial and institutional use only. **KEEP OUT OF THE REACH OF CHILDREN.** See Material Safety Data Sheet (MSDS) for more complete information.

### GUARANTEE

Cantol guarantees its products, when used as directed, to do all it claims. Should the product fail to demonstrate our claims, the remaining material may be returned to us and no charge will be made.